



YARNS POLIAMIDE TEXTURED TWISTED HEAT-SET

Application: intended for the production of carpets and other products.

Name properties	Norm for yarns
Yarn structure	180 tex x 2, 130 tex x 2, 120 tex x 2, 120 tex x 1, 115 tex x 2, 110 tex x 2, 100 tex x 2
Deviation of standard linear density from nominal, %	± 5
Tenacity, MH/текс, не менее - for shiny, matte - for bulk dyed	200,0 160,0
Elongation at break, %	40,0 - 55,0
Twist direction	Z (or S)
Linear shrinkage, %, max	4,0
Number of twists, pcs/m	(50 - 300) ±15

Package: block package on pallets.